



NOTES:

1. REPLACED ROCK MATERIAL OVER DITCH SHALL BE TWICE THE THICKNESS OF THE ORIGINAL ROCK. (12" MIN. & 18" MAX.)
2. ROCK MATERIAL SHALL BE PLACED IN 6" LAYERS AND EACH LAYER COMPACTED TO 98% DENSITY PER A.A.S.H.T.O. T-180.
3. SUBGRADE MATERIAL ABOVE PIPE SHALL BE PLACED IN A 6" LAYERS AND COMPACTED TO 98% DENSITY PER A.A.S.H.T.O. T-180.
4. ASPHALT CONCRETE PAVEMENT JOINTS SHALL BE MECHANICALLY SAWED.
5. BASE MATERIAL SHALL HAVE A MINIMUM LBR OF 100 AND A MINIMUM CARBONATE CONTENT OF 70%.
6. IF THE DITCH IS FILLED TEMPORARILY, IT SHALL BE COVERED WITH A 1 1/2" MIN. THICK ASPHALTIC CONCRETE PATCH TO KEEP THE FILL MATERIAL FROM RAVELING, UNTIL PLACED WITH A PERMANENT PATCH.
7. PERMANENT ASPHALT REPLACEMENT SHOULD BE TWICE EXISTING THICKNESS, 1 1/2" MINIMUM TYPE S-III ASPHALT OVERLAY.

CITY OF PLANTATION ENGINEERING STANDARDS PLANTATION, FLORIDA	SCALE: N.T.S.	CUT AND RESTORE TRENCH DETAIL AND NOTES
	REVISED: 11/12/09	